



23010 Ryen Dr NW, Ste C. • Poulsbo, WA 98370-6406
(360) 598-3090 • FAX (206) 494-7787
email: info@tarpinnovators.com

PRODUCT SPECIFICATION SHEET

Q1212 - 8 oz FR

General Description:

BASE FABRIC

Denier of Tapes: 1600D (Black)
Construction (tapes/inch): warp 12 / weft 12
Weight: 8 oz psy

TEST METHOD

COATED FABRIC

Coating: 2 mil / both sides
Thickness: 15 mil
Standard Width: 144"
Standard Color: Grey

MECHANICAL PROPERTIES

Tensile Grab Strength:	230/230	ASTM D5034
Grab Tear:	warp 60 / weft 70	ASTM D751
Burst:	460 PSI	ASTM D3786
Puncture:	140lbs	ASTM D4833
Fire Retardant:	2 second self-extinguish	CPAI 84 Section 6
	2 second self-extinguish	NFPA 701
Weatherability:	Special UVI treatment gives 60% strength retention after 2000 hours in a weatherometer.	